

## 1. Product Information

Supplier: JIANGSU CHANGJING ELECTRONICS TECHNOLOGY CO.,LTD.

|                          |             |
|--------------------------|-------------|
| <b>Part Number:</b>      | CJ3401A     |
| <b>Package Type:</b>     | SOT-23      |
| <b>Part Description:</b> | SMD/MOSFET  |
| <b>Report Date:</b>      | August-2025 |

## 2. Reliability Test Results: PASS

| Test Item   | Test Condition  | Duration                     | Fail Quantity / S.S |
|---|---|------------------------------|---------------------|
| Pre-and post-stress Electrical test                   | Ta=25°C   | —                            | All parts           |
| <b>PC</b><br>Precondition(For SMD Package Only)       | JESD22-A113F/J-STD-020<br>1.Bake:125°C<br>2.Soak:<br>85°C85%RH,168Hours MSL1<br>or<br>30°C60%RH,192Hours MSL3<br>3.Reflow 3Cycles Max 260°C<br>4.all samples E-Test | >168Hours<br>or<br>>192Hours | 0 / 308             |
| <b>TCT</b><br>Temperature Cycling Test                | JESD22 -A104<br>-55°C/15min 150°C/15min   | 1000Cycles                   | 0 / 77              |
| <b>AC</b><br>Autoclave                                | JESD22-A102<br>121°C, 100%RH  | 96Hours                      | —                   |
| <b>UHA</b><br>Unbiased Highly Accelerated Stress Test | JESD22-A118<br>130°C, 85%RH   | 96Hours                      | 0 / 77              |
| <b>HT</b><br>High Humidity &Temp. Test                | JESD22-A101<br>85°C 85%RH   | 1000Hours                    | 0 / 77              |
| <b>HTST</b><br>High Temperature Storage Test          | JESD22 -A103<br>T=Tstg max  | 1000Hours                    | 0 / 77              |
| <b>H3TRB</b><br>High Humidity &Temp. Bias Test        | JESD22-A101<br>85°C 85%RH VDS*80% VDS≤100V Max  | 1000Hours                    | —                   |
| <b>HAST</b><br>Highly Accelerated Stress Test         | JESD22-A110<br>130°C 85%RH VDS*80% VDS≤42V Max  | 96Hours                      | 0 / 77              |
| <b>HTRB</b><br>High Temperature Revers Bias Test      | JESD22 -A108<br>Tj(max), VDS*80%  | 1000Hours                    | 0 / 77              |
| <b>HTGB</b><br>High Temperature Gate Bias Test        | JESD22 -A108<br>Tj(max), VGS*100%   | 1000Hours                    | 0 / 77              |
| <b>IOL</b><br>Intermittent Operational Life           | MIL-STD-750D Method 1037<br>ΔTj≥100°C, On/Off:2min  | 15000Cycles                  | 0 / 77              |
| <b>RSH</b><br>Resistance to Solder Heat test          | JESD22-A111B<br>260°C±5°C, 10(+2,-0)Seconds   | —                            | 0 / 30              |
| <b>SD</b><br>Solderability                            | J-STD-002<br>1.Steam aging: 93°C 8Hours<br>2.245°C 3~5s   | —                            | 0 / 10              |

### Notes:

1. Either H3TRB or HAST for reliability test.
2. Either AC or UHA for reliability test.
3. Detailed MSL of the product refers to the MSL Report.

Remark: JSCJ Laboratory reserves the right of final interpretation of this report